

Materialgruppen Material groups Groupes matières	P		H				K			
Materialgruppen Material groups Groupes matières	Wenig legierter Stahl <1400 N/mm Low-alloyed steel <1400 N/mm Acier faible allié <1400N/mm		Stahl 45-55HRC Steel 45-55HRC Acier 45-55HRC	Stahl 55-60 HRC Steel 55-60 HRC Acier 55-60 HRC	Stahl 60-65 HRC Steel 60-65 HRC Acier 60-65 HRC	Stahl 60-65 HRC Steel 60-65 HRC Acier 60-65 HRC	Gusseisen Cast Iron Fonte			
Vc m/min	8-15		8-10	6-8	4-6	15-20				
f mm/U 1,0-2,99	0,025	0,035	0,030	0,050	0,020	0,030	0,020	0,030	0,060	0,090
f mm/U 3,0-5,99	0,035	0,090	0,050	0,120	0,030	0,075	0,030	0,075	0,090	0,180
f mm/U 6,0-7,99	0,090	0,100	0,120	0,150	0,075	0,090	0,075	0,090	0,180	0,250
f mm/U 8,0-9,99	0,100	0,120	0,150	0,160	0,090	0,100	0,090	0,100	0,250	0,260
f mm/U 10,0-12,0	0,120	0,140	0,160	0,170	0,100	0,110	0,100	0,110	0,260	0,280